

Waterproofing admixture for concrete

Idrocrete DM is a liquid waterproofing admixture for cementitious mixtures that significantly reduces the absorption of water in cured concrete and prevents efflorescences.

WHERE TO USE

Idrocrete DM is especially recommended for all applications which require increased impermeability.

Use **Idrocrete DM** to prepare concrete with a low degree of water absorption and to prevent the appearance of surface efflorescence.

Idrocrete DM is especially recommended as an integral waterproofer for vibrated concrete such as concrete blocks, sump pits, kerbstones, pavers, etc.

Some application examples

- Concrete foundations.
- Concrete for supporting wall.
- Concrete for underground structures (basements, lift wells, ditches).
- Concrete for sewage treatment tanks, cisterns, canals, etc.

ale la

- Vibrated concrete.
- Precast concrete.





TECHNICAL CHARACTERISTICS

Idrocrete DM is an admixture with a base of special waterproofing agents manufactured from a formula developed in the MAPEI research laboratories.

Idrocrete DM, when used in amounts of $0.2 \div 1\%$ by weight of cement, does not alter the performance of fresh concrete or the development of mechanical strength.

Idrocrete DM can be used in combination with plasticisers and superplasticisers of the Mapeplast, Mapemix, and Mapefluid lines to prepare fluid and super-fluid waterproof grout and concrete and to improve the mechanical performance of the cement mix when cured.

APPLICATION PROCEDURE

Add **Idrocrete DM** into the mixer after the other ingredients (water, cement and aggregates) and mix until a homogeneous paste is obtained.

Idrocrete DM can, however, be added with the rest of the ingredients if necessary, because its water-repellent effect remains unaltered regardless of when it is mixed.

Before using refer to the product's safety data sheet.

CONSUMPTION

Dosage by weight:

From 0.21 to 1.06 litres for every 100 kg of cement.

Dosage by volume:

From 0.2 to 1 litre for every 100 kg of cement.

PACKAGING

Idrocrete DM is available in 25 kg and 200 litre drums, 1000 litre tanks, and in bulk.

STORAGE

Stored in closed containers, **Idrocrete DM** is stable for at least 12 months. Protect from frost and sunlight.

FOR PROFESSIONALS.

WARNING

Although the technical details and recommendations contained in this report correspond to the best of our knowledge and experience, all the above information must, in every case be taken as merely indicative and subject to confirmation after long-term practical applications; for this reason, anyone who intends to use the product must ensure beforehand that it is suitable for the envisaged application. In every case, the user alone is fully responsible for any consequences deriving from the use of the product.


All relevant references of the product are available upon request

PERFORMANCE DATA FOR IDROCRETE DM

A) CONCRETE COMPOSITION

COMPOSITION	1	2	3	4
CEM II/A-L 32.5 R (kg/m³)	350	350	350	350
Aggregate 0 to 8 mm (kg/m³)	1830	1830	1830	1830
Water (kg/m³)	180	180	180	180
Idrocrete DM (I/m³)	-	0.9	1.8	3.5

B) WATER ABSORPTION TESTS (UNI 7699)



TECHNICAL DATA (typical values)			
PRODUCT IDENTITY			
Consistency:	liquid		
Colour:	white		
Density (ISO 758) (kg/l):	1.03 ± 0.02 at +20°C		
Dry solids content (EN 480/8) (%):	50 ± 2.5		
Specific action:	increases impermeability and reduces efflorescence		
Classification:	water resisting admixture according to EN 934-2 table 9		
Chlorides (EN 480/10):	absent		
Storage:	12 months in original sealed packaging. Protect from frost		
Hazard classification according to EC 99/45:	none		
Customs class:	3824 40 00		





MAPEI GROUP CERTIFIED MANAGEMENT SYSTEMS (Quality, Environment and Safety)











MAPEI FAR EAST Pte Ltd

MAPEI ARGENTINA S.A.







ELEMIE DE



RESCON MAPEI AS - NORWAY







MAPEI INC - CANADA





MAPEI SUISSE SA

www.mapei.com